

# ASLAN SL 95

## The clear anti-graffiti laminating film

This highly transparent, clear laminating film protects valuable prints and photos long-termed from ultraviolet rays, vandalism and other external influences. Its special coating makes this laminate dirt-repellent and easy to clean. Graffitis can be easily removed from the surface.

For any further information please contact our technical advisory service:  
**+49 (0)2204.708-80**

### CONSTRUCTION

<b>face-film:</b>	PET (with special varnish)	
<b>thickness:</b>	~ 50 µm	
<b>adhesive:</b>	acrylic pressure adhesive	square quantity: ~ 25 g/m <sup>2</sup>
<b>release liner:</b>	siliconised PE-release liner	square weight: ~ 64 g/m <sup>2</sup>

### CHARACTERISTICS

<b>adhesive strength: (ASTMD-903)</b>	immediately after 1 week	~ 5 N/25 mm ~ 10 N/25 mm
<b>dimensional stability:</b>	applicated onto aluminium after 48 hours stored at 70 °C (25 x 25 cm)	max. -0.05 %
<b>chemical resistance:</b>	In a preece test of 24 hours the applied film is resistant to most petroleum based oils, greases and aliphatic solvents, mild acids, alkalies and salts.	
<b>temperature:</b>	application temperature: service temperature range:	min. 15°C -30 °C up to +80 °C
<b>minimum durability:</b>	5 years outdoors, with vertical exposure, in middle-european normal climate.	

# ASLAN SL 95

## PROCESSING

<b>application:</b>	Dry application only.
<b>storage life:</b>	Before application the films can be stored for minimum 3 years from date of production. The film must be stored at room temperature (15-25 °C) and a relative humidity of the air of 50-60%. To avoid pressure points appearing on the roll surface, we recommend the rolls be stored either vertical standing or for this purpose designed 'hanging' racks.

state: 06|2011

---

All technical data and advice is based on our experience and measured testing that we believe to be reliable. It remains the customer's responsibility to test our products suitability for the purpose intended.

The quality of our products is regularly examined, upgraded and developed. We reserve the right, without prior notice, to adjust, upgrade and improve the chemical structures or physical characteristics of their products in accordance with their latest knowledge.

---

### **ASLAN, Schwarz GmbH & Co. KG**

POB 5165 · D-51486 Overath · Oberauel 2 · D-51491 Overath · Germany  
**fon** +49 (0) 2204. 708-80 · **fax** +49 (0) 2204. 708-50 · **e-mail** info@ASLAN-schwarz.com

**[www.ASLAN-schwarz.com](http://www.ASLAN-schwarz.com)**