

ASLAN 85 K

The high flexible stencil film for tarpaulin and vehicles

This self-adhesive stencil film is ideal for lacquering and painting works on smooth surfaces. Its matt, grey and transparent surface is inscribable and makes it easier to label the work area.

Its high flexibility adapts easily to edges and curves. A special adhesive ensures an easy removability without residues and allows overlapping paintings and multi-colour laquerings even on touchdry paints.

This high quality film is excellent for the use in computerised cutting of shapes and lettering.

For any further information please contact our technical advisory service:
+49 (0)2204.708-80

CONSTRUCTION

face-film:	soft PVC	
thickness:	~ 80 µm	
adhesive:	acrylic pressure adhesive	square quantity: ~ 16 g/m ²
release liner:	silicon cardbord	square weight: ~ 140 g/m ²

CHARACTERISTICS

adhesive strength: (ASTMD-903)	immediately: 1 week adhered:	~1 N/25mm ~2 N/25mm
dimensional stability:	applicated onto acrylic glass after 2 h stored at 70°C	no longitudinal and lateral shrinkage
tensile strenght:	DIN 53 455	longitudal: ~150 % lateral: ~170 %
combustibility:	stuck on aluminium, the film is self-extinguishing.	
temperature:	application temperature service temperature range	min. 15°C -30°C up to +80°C

ASLAN 85 K

PROCESSING

- application:** Dry application only. Humidity, longer application processes and high temperatures increase the adhesive strenght.
- For the application of letterings etc. we recommend one of our ASLAN application tapes e.g. ASLAN TMO.
- storage properties:** Before application the foils can be stored for minimum 3 years from date of production. The film must be stored at room temperature (15-25 °C) and a relativ humidity of the air of 50-60%. To avoid pressure points appearing on the roll surface, we recommend the rolls be stored either vertical standing or for this purpose designed 'hanging' racks.

state: 11|2008

All technical data and advice is based on our experience and measured testing that we believe to be reliable. It remains the customer's responsibility to test our products suitability for the purpose intended.

The quality of our products is regularly examined, upgraded and developed. We reserve the right, without prior notice, to adjust, upgrade and improve the chemical structures or physical characteristics of their products in accordance with their latest knowledge.

ASLAN, Schwarz GmbH & Co. KG

POB 5165 · D-51486 Overath · Oberauel 2 · D-51491 Overath · Germany
fon +49(0)2204.708-80 · **fax** +49(0)2204.708-50 · **e-mail** info@ASLAN-schwarz.com

www.ASLAN-schwarz.com