

KIWALITE Promotional Grade 9500

Technical Bulletin

Description

KIWA

enclosed reflective sheeting featuring good reflectivity and durability for a even better price

Application Range

perfect for stickers, emblems or short-term safety signs

•••

Colors

white, yellow, orange, red, green, blue



Photometric Property

| | | Initial Value | | | | | | |
|----------------------|------|---------------|-------|--------|--------|-------|-------|-------|
| | D.A. | I.A. | White | Yellow | Orange | Red | Green | Blue |
| Reflectivity | | 5° | 52.2 | 42.6 | 29.7 | 15.1 | 13.9 | 5.8 |
| | 0.2° | +30° | 40.1 | 32.7 | 21.3 | 11.2 | 9.9 | 4.1 |
| | | +40° | 31.4 | 25.4 | 16.3 | 8.5 | 7.3 | 3.1 |
| Chromaticity | Ý | | 39.9 | 27.4 | 15.7 | 9.1 | 5.3 | 3.2 |
| (Light source – D65) | | х | 0.299 | 0.495 | 0.582 | 0.637 | 0.165 | 0.159 |
| | | V | 0.320 | 0.482 | 0.396 | 0.332 | 0.512 | 0.139 |

Accelerated Weathering Test

| Reflectivity after 300 h Sunshine Weather-O-Meter | D.A. | I.A. | White | Yellow | Orange | Red | Green | Blue |
|---|------|------|-------|--------|--------|-------|-------|-------|
| | 0.2° | 5° | 50.6 | 39.9 | 27.0 | 14.3 | 12.9 | 5.7 |
| | | +30° | 38.6 | 30.1 | 20.3 | 10.3 | 9.0 | 3.8 |
| | | +40° | 30.6 | 24.1 | 15.7 | 7.8 | 6.6 | 2.8 |
| Chromaticity | Ý | | 39.7 | 27.1 | 15.0 | 8.7 | 4.8 | 3.0 |
| (Light source – D65) | > | (| 0.300 | 0.494 | 0.580 | 0.635 | 0.167 | 0.160 |
| | 1 | 1 | 0.321 | 0 483 | 0.397 | 0.333 | 0.507 | 0 139 |

Folie & Papper Sweden AB Box 9024 400 91 Göteborg
 Telefon
 031-49 00 80, 08-785 04 23

 Fax
 031-49 00 89

www.foliepapper.se



KIWA

| Thickness | | 100 100 |
|-------------------------|-----------------|---------------|
| (without release liner) | | 122 ~ 128 μm |
| Weight | | 192 ~ 202 g/m |
| Adhesion test | Aluminium | 13.0 N/inch |
| | Stainless steel | 10.0 N/inch |
| | Sheet on sheet | 9.8 N/inch |
| Elongation | | 25% ~ 45% |
| Solvent Resistance | | |
| water at 98°C | 5 min | no effect |
| 10% Hydrochloric Acid | 5 min | no effect |
| 10% Ammonium Hydroxide | 5 min | no effect |
| Gasoline | 30 min | no effect |
| Kerosine | 10 min | no effect |
| Turpentine Oil | 10 min | no effect |
| Methyl alcohol | 10 min | no effect |
| Mineral Spirits | 10 min | no effect |

Please notice that substrates have to be free of dust and silicones, furthermore prints have to be completely cured, otherwise adhesion cannot be guaranteed. It is advisable to carry out some application tests to check the compatibility with different types of substrate. Please adhere to the manufacturer's application instructions.

All the technical information given herein are based on tests we have conducted, but the accuracy nor completeness is not guaranteed. Before using, user shall determine the suitability of the product for his intended use and user assumes all risk and liability.

Folie & Papper Sweden AB Box 9024 400 91 Göteborg
 Telefon
 031-49 00 80,08-785 04 23

 Fax
 031-49 00 89

www.foliepapper.se